

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
20 December 2001 (20.12.2001)

PCT

(10) International Publication Number  
**WO 01/96419 A2**

- (51) International Patent Classification<sup>7</sup>: C08F 10/02
- (21) International Application Number: PCT/GB01/02650
- (22) International Filing Date: 14 June 2001 (14.06.2001)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:  
0014547.4 14 June 2000 (14.06.2000) GB
- (71) Applicant (for all designated States except US): **BOREALIS TECHNOLOGY OY** [FI/FI]; P.O. Box 330, FIN-06101 Porvoo (FI).
- (71) Applicant (for GB only): **GOLDING, Louise** [GB/GB]; c/o 179 Queen Victoria Street, London EC4V 4EL (GB).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): **BAANN, Hege, Vale** [NO/NO]; Planerveien 34, N-3942 Skjelsvik (NO). **LIN-DAHL, Ann, Kristin** [NO/NO]; Skienstgate 32, N-3912 Porsgrunn (NO).
- (74) Agents: **GOLDING, Louise et al.**; Frank B. Dehn & Co., 179 Queen Victoria Street, London EC4V 4EL (GB).
- (81) Designated States (national): AE, AG, AL, AM, AT, AT (utility model), AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, CZ (utility model), DE, DE (utility model), DK, DK (utility model), DM, DZ, EC, EE, EE (utility model), ES, FI, FI (utility model), GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SK (utility model), SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.
- (84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

**Published:**

— without international search report and to be republished upon receipt of that report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

WO 01/96419 A2

(54) Title: INJECTION MOULDING POLYMER

(57) Abstract: The invention relates to the use of an LLDPE produced using a single site catalyst, e.g. an LLDPE produced using a metallocene (m-LLDPE), in injection moulding of food packaging material, especially closures for food containers. Such materials have been found to exhibit low levels of migration, typically less than 40 mg/dm<sup>2</sup>, e.g. less than 5 mg/dm<sup>2</sup>, and are particularly suitable for use in packaging foods having a high fat content.

Injection Moulding Polymer

5 The present invention relates to improvements in or relating to linear low density polyethylenes (LLDPEs), in particular to the use of LLDPEs for injection moulding and to products obtainable thereby.

10 LLDPEs are widely used in the manufacture of packaging products, which are typically produced by moulding techniques, especially injection moulding. LLDPE materials used for these purposes are typically produced using conventional Ziegler-Natta catalysts.

15 In cases where an injection moulded LLDPE product is to be used in critical applications, e.g. in the packaging of food or medical products, particularly as closure means (e.g. lids) for food containers, it is essential that this should not contaminate the packaged product. For food packaging applications, an indication of the degree of contamination may be obtained from  
20 tests which determine the level of migration of the polymer material, e.g. when immersed in a fatty food simulant such as olive oil. In the case of LLDPEs prepared using Ziegler-Natta catalysts the levels of migration have been found to be too high to permit their  
25 use in the production of injection moulded packaging materials for food and medical products, especially fatty foods.

Surprisingly, we have now found that by using LLDPEs produced using a single site catalyst, in  
30 particular those produced using a metallocene catalyst (m-LLDPEs), it is possible to produce moulded products (e.g. injection moulded products) having acceptable migration levels for use in packaging food and medical products, especially for use in packaging foods having a  
35 high fat content, such as cheese, mayonnaise, ketchup, butter, etc.

Thus viewed from one aspect the invention provides

- 2 -

the use of an LLDPE produced using a single site catalyst, in particular an LLDPE produced using a metallocene (m-LLDPE), in injection moulding of food packaging material, especially closures for food  
5 containers.

Particularly preferred for use in the invention are LLDPEs having a relatively narrow molecular weight distribution or MWD (i.e. the ratio of the weight average molecular weight to the number average molecular weight), e.g. those having a MWD ranging from 2 to 60,  
10 preferably from 3 to 10, more preferably from 3 to 6.

Viewed from a further aspect the invention provides an injection moulded article, e.g. an injection moulded closure, particularly a closure for a food container,  
15 formed from an LLDPE produced using a single site catalyst, preferably from a metallocene LLDPE, said LLDPE preferably having a MWD in the range of from 2 to 60, preferably from 3 to 10, more preferably from 3 to 6.

LLDPE materials which have been found to be particularly suitable for use in the production of injection moulded packaging materials for food and medical products are those having migration levels of less than  $40\text{mg/dm}^2$ , preferably less than  $10\text{mg/dm}^2$ , e.g.  
20 less than  $5\text{mg/dm}^2$ .

Viewed from a further aspect the invention thus provides an LLDPE, e.g. a metallocene LLDPE, suitable for use in injection moulding having a migration level of less than  $40\text{mg/dm}^2$ , preferably less than  $10\text{mg/dm}^2$ ,  
25 e.g. less than  $5\text{mg/dm}^2$ .

Viewed from a still further aspect the invention provides the use of an LLDPE, e.g. a metallocene LLDPE, in forming an article, preferably a closure for a container, having a migration level of less than  
30  $40\text{mg/dm}^2$ , preferably less than  $10\text{mg/dm}^2$ , e.g. less than  $5\text{mg/dm}^2$ .

By polyethylene is meant a polymer the majority by

- 3 -

weight of which derives from ethylene monomer units. A minor proportion, e.g. not more than 20% by weight, more preferably not more than 15% by weight, of the polymer may derive from other monomers copolymerisable with ethylene. Suitable comonomers include those selected from C<sub>3-20</sub> mono or multiple unsaturated monomers, in particular C<sub>3-10</sub>  $\alpha$ -olefins, e.g. propene, but-1-ene, pent-1-ene, 3-methyl-but-1-ene, 4-methyl-pent-1-ene, hex-1-ene, 3,4-dimethyl-but-1-ene, hept-1-ene, 3-methyl-hex-1-ene, etc. Preferably the monomers will be selected from propene, but-1-ene, hex-1-ene and oct-1-ene. As used herein, ethylene copolymer is intended to encompass a polyethylene deriving from ethylene and one or more monomers copolymerisable with ethylene.

The polyethylene may also contain minor amounts, e.g. not more than 10% by weight, preferably not more than 5% by weight, of other polymers, e.g. other polyolefins such as polypropylenes. Conventional additives such as antioxidants, UV-stabilizers, colours, fillers, etc., generally in amounts of up to 10% by weight, e.g. up to 5% by weight, may also be present.

By LLDPE is meant a polyethylene having a density of 890 to 940 kg/m<sup>3</sup>, preferably 915 to 930 kg/m<sup>3</sup>, especially 917 to 926 kg/m<sup>3</sup>, and a crystallinity of 20 to 60%, preferably 30 to 50%, especially 40 to 50%.

LLDPEs useful in the invention include mono-modal, bi-modal and multi-modal polymers. Mono-modal polymers, which are typically characterised by a narrow molecular weight distribution, may be advantageous. Typically a mono-modal polymer having a narrow MWD will be produced in a single polymerization stage under a single set of processing conditions (temperature, pressure, etc.) using a single monomer and a single polymerization catalyst.

Bi-modal and multi-modal LLDPEs useful in the invention may be produced by blending two or more mono-

- 4 -

modal polyethylenes having different MWDs.

Alternatively and preferably, they may be produced by polymerization under conditions which create a bi-modal or multi-modal polymer, e.g. using two or more single  
5 site catalysts and/or using a catalyst system or mixture with two or more different catalytic sites, or using two or more polymerization stages in which the reactants are subjected to different reaction conditions (e.g. different temperatures, pressures, polymerization media,  
10 hydrogen partial pressures, etc.) (see EP-A-778289).

The or each polymerization stage used to produce LLDPEs for use in the invention may be effected using conventional ethylene homo- or co-polymerization procedures such as slurry, gas phase or solution  
15 polymerization, gas phase polymerization being preferred. The polymerization process may use one or more conventional reactors, e.g. loop reactors, gas phase reactors, etc. For gas phase reactors, the reaction temperature used will generally be in the range  
20 60 to 115°C (e.g. 70 to 110°C), the reactor pressure will generally be in the range 10 to 25 bar, and the residence time will generally be 1 to 8 hours. The gas used will commonly be a non-reactive gas such as nitrogen together with monomer. Hydrogen may also be  
25 present to further control the molecular weight of the polymer produced in the reactor. Molecular weight control may be effected through control of the hydrogen concentration or, alternatively, through control of the hydrogen consumption during the polymerization process.

30 Bi-modal (or multi-modal) LLDPE may be produced using a multi-stage polymerization process, e.g. using a series of reactors in which comonomer may be added in only the reactor(s) used for production of the higher (or highest) molecular weight component(s). A first  
35 polymerization stage may be carried out in a slurry loop reactor, typically operated at 80 to 100°C and a

- 5 -

containing the active catalyst, is continuously withdrawn, separated from the reaction medium and transferred to a gas phase reactor in which a second polymerization stage is carried out. The second gas  
5 phase reactor is usually operated at 80 to 90°C and a pressure of from 25 to 30 bar.

Catalysts for use in producing LLDPEs useful in the invention may be selected from conventional single site catalysts. By single site catalyst is meant a catalyst  
10 which provides a single type of catalytically effective site at which polymer chain extension occurs. Particularly preferred as single site catalysts are the metallocenes, optionally supported on inorganic or organic substrates, in particular on porous oxides such  
15 as silica, alumina or silica-alumina. Advantageously these may also be used in combination with a co-catalyst, particularly preferably an aluminoxane.

The term metallocene as used herein is used to refer to any catalytically active complex containing one  
20 or more  $\eta$ -ligands. The metal in such complexes is preferably a group 4, 5, 6, 7 or 8 metal or a lanthanide or actinide, especially a group 4, 5 or 6 metal, particularly Zr, Hf, Ti or Cr, particularly preferably Zr or Hf. The  $\eta$ -ligand preferably comprises a  
25 cyclopentadienyl ring, optionally with a ring carbon replaced by a heteroatom (e.g. N, B, S or P), optionally substituted by pendant or fused ring substituents and optionally linked by a bridge (e.g. a 1 to 4 atom bridge such as  $(CH_2)_2$ ,  $C(CH_3)_2$  or  $Si(CH_3)_2$ ) to a further  
30 optionally substituted homo or heterocyclic cyclopentadienyl ring. The ring substituents may for example be halo atoms or alkyl groups optionally with carbons replaced by heteroatoms such as O, N and Si, especially Si and O and optionally substituted by mono  
35 or polycyclic groups such as phenyl or naphthyl groups.

Suitable metallocenes and aluminoxane co-catalysts are well known from the scientific and patent

- 6 -

literature, e.g. from the published patent applications of Hoechst, Montell, Borealis, Exxon and Dow.

LLDPEs used according to the invention will preferably have the following properties:

- 5 MFR<sub>2.16</sub>: 20 to 100, preferably 30 to 80, e.g. 30 to 50;  
Density: 910 to 930 kg/m<sup>3</sup>, preferably 920 to 930 kg/m<sup>3</sup>;  
Mw (weight average molecular weight): 20 to 100 kD,  
preferably 40 to 50 kD;  
10 Mn (number average molecular weight): 5 to 30 kD,  
preferably 10 to 15 kD;  
MWD (i.e. the ratio of the weight average molecular  
weight to the number average molecular weight): 3 to 10,  
more preferably 3 to 6.  
15 E-modulus: >180 MPa, preferably 200 to 300 MPa;  
Tensile impact strength: 50 to 300 KJ/m<sup>2</sup>, preferably >100  
KJ/m<sup>2</sup>;  
Elongation at break: >400%;  
Tensile stress at yield: 5 to 15 MPa, preferably 7 to 10  
20 MPa;  
Vicat Softening Temperature (10N): 75 to 150°C,  
preferably 85 to 100°C.

- LLDPEs may, for example, be injection moulded in  
25 accordance with the invention using conventional  
injection moulding equipment, e.g. operating at  
injection temperatures of 180 to 280°C, e.g. about 200°C  
and injection speeds in the range of from 10 to 500  
mm/sec, preferably about 100 mm/sec. Suitable mould  
30 temperatures may range from 0 to 80°C. Closures  
produced in this way will typically have maximum  
dimensions in the range of 5 to 1000 mm.

- Viewed from a further aspect the invention thus  
provides a closure for a food container, which closure  
35 is formed from an LLDPE as herein described, e.g. a  
metallocene LLDPE, preferably an LLDPE having a  
migration level of less than 40mg/dm<sup>2</sup> preferably less

than 10mg/dm<sup>2</sup>, e.g. less than 5mg/dm<sup>2</sup>.

Closures produced using LLDPEs as herein described are particularly suitable for use in packaging of foods, e.g. bread, salads, cakes, puddings, soups, cheese, mayonnaise, ketchup, butter, etc., especially foods having a high fat content. They may also be suitable for use in packaging medical products in cases where it is important that migration of the polymer material should be prevented, e.g. in packaging of solutions, suspensions, emulsions, syrups, etc.

The LLDPE products herein described are particularly suited to use as closures, e.g. caps or lids, where a degree of flexibility is necessary for their removal by the consumer. In such cases, the products may be used in conjunction with, for example, plastic (e.g. polypropylene), glass or metal containers.

The invention will now be further described with reference to the following non-limiting Examples.

#### Example 1 - Catalyst Preparation

All reactions were carried out under a nitrogen atmosphere. 40 ml of a 30% solution of methylaluminoxane (MAO) in toluene was diluted with 40 ml of toluene. The resulting solution was added to 22.6 g of rac-(ethylenebis(2-(tert-butyl)dimethylsiloxy)indenyl))zirconium dichloride (ABO<sub>3</sub>Cl<sub>2</sub>). This MAO/metallocene solution was combined with another 1250 ml of a 30% w/w solution of MAO. After a reaction time of 10 minutes the total volume of solution was added to 1000 g of silica placed in a reactor under an inert atmosphere. The resulting mixture was allowed to react for 90 minutes. Drying was effected by flushing with nitrogen and simultaneously heating the reaction vessel to 85°C for 18 hours. The thus-obtained catalyst was a dry, free-flowing powder.



- 8 -

Example 2 - Polymer Preparation and Properties

Ethylene, hexene, hydrogen and nitrogen together with a polymerization catalyst prepared in accordance with Example 1 were fed to a gas phase reactor with fluidised bed operating at 75°C and 17.5 bar. Polymer production rate was approx. 10-11 kg PE/h. Circulation gas velocity was maintained at about 2200 kg/h and the bed level was 2.0 m.

Polymerization parameters are set out in the following Table 1:

Table 1

	Sample 1	Sample 2	Sample 3
Ethylene feed (kg/h)	17.9	16.2	17.1
Ethylene partial pressure (bar)	14.8	14.7	13.9
Hydrogen feed (kg/h)	0.001	0.001	0.0014
H <sub>2</sub> /C <sub>2</sub> (*100)	0.122	0.2	0.13
Hexene feed (kg/h)	1.2	1.2	1.1
Hexene/C <sub>2</sub> (*100)	1.5	1.9	1.5
Production rate (kg/h)	11.0	9.6	11.0

Properties of the polymer products compared to those of an LLDPE product obtained using the Ziegler-Natta (Z/N) catalyst M-cat (UCC) are set out below in Table 2:

Table 2

	Sample 1	Sample 2	Sample 3	Z/N- derived polymer
MFR <sub>2.16</sub> (g/10 min) <sup>1</sup>	31	51	48	28
Density (kg/m <sup>3</sup> ) <sup>2</sup>	926	921	921	919
5 Mw <sup>3</sup>	49000	41000	41000	55000
Mn <sup>3</sup>	12000	11000	13000	10000
MWD <sup>3</sup>	4.1	3.8	3.2	5.4
E-modulus (MPa) <sup>4</sup>	280	230	220	180
10 Tensile impact strength (KJ/m <sup>2</sup> ) <sup>5</sup>	130	170	170	110
Elongation at break (%) <sup>6</sup>	>400	>400	>400	>400
Tensile stress at yield (MPa) <sup>7</sup>	10	8.7	8.5	7.5
15 Vicat (°C) <sup>8</sup>	98	91	90	82

<sup>1</sup>MFR<sub>2.16</sub> determined at 190°C using 2.16 kg load according to ISO 1133.

<sup>2</sup>Density determined using ISO 1183

20 <sup>3</sup>Mw, Mn and MWD measured by GPC equipment (gel permeation chromatography, size exclusion chromatography) according to BTM 15521 (Borealis) at 140°C, solvent: trichlorobenzene (Flowrate: 1.0 ml/min). See H.G. Barth and J.M. Mays (Eds.): Modern Methods of Polymer  
25 Characterization (Chemical Analysis Vol. 113), John Wiley & Sons, 1991.

<sup>4</sup>E-modulus determined using ISO 527-2

<sup>5</sup>Tensile impact strength determined according to ISO 8256/A1

30 <sup>6</sup>Elongation at break determined according to ISO 527-2

<sup>7</sup>Tensile stress at yield determined according to ISO 527-2

<sup>8</sup>Vicat determined according to ISO 306

Example 3 - Injection Moulding

Using Samples 1, 2 and 3 produced in accordance with Example 2, test specimens (lids) were produced by injection moulding on a Netstal 300 injection moulding machine according to the following parameters:

Melt temperature: 200°C

Standard screw: 70 mm/25D

10 Injection speed: 100mm/sec

Hold-on pressure: 3 sec

Cooling time: 5 sec

Mould temperature: 30°C (injection side)

15°C (cavity side)

15

Migration tests on the moulded products were performed in olive oil for 10 days at 40°C (total immersion).

Hexane extractables were determined by extraction in n-hexane at 50°C for 2 hours. Results are set out in

20 Table 3 below:

Table 3

	Sample 1	Sample 2	Sample 3	Z/N-derived polymer
25 Global migration (mg/dm <sup>2</sup> ) <sup>1</sup>	0.5 and -3.9	-	-	48.8 and 45.3
Hexane extractables (% w/w) <sup>2</sup>	0.91	1.2	1.2	5.3

<sup>1</sup>Migration determined according to ENV 1186-2 (ENV = European pre-standard)

<sup>2</sup>Hexane extractables determined according to FDA (US) standard 177.1520

35 All products were found to exhibit low warpage and distortion.

- 11 -

Example 4 - Migration data for compression moulded LLDPE samples

1 mm thick compression moulded sheets of a variety of polyethylene grades prepared using single site metallocene catalysts and (for comparative purposes) of one grade produced using a Ziegler-Natta catalyst were subjected to migration tests by immersion in olive oil at 40°C for 10 days. The results are shown in Table 4 below:

Table 4

Producer	Product	MFR <sub>2</sub> (at 190°C)	Density (kg/m <sup>3</sup> )	Migration (mg/dm <sup>2</sup> )
Fina	Finacene 2245ER	0.9	933	-9.2
Dow	Elite 5400	0.8	917	-5.1
Mitsui	Evolue SP2520	1.8	925	-6.1
Borealis	POKO 1082 <sup>(1)</sup>	1.2	914	-9.7
Borealis	Borecene ME8160 <sup>(2)</sup>	6	940	-6.6
Borealis	Si1-7059 <sup>(3)</sup>	31	926	-3.9
Borealis	LE8030 <sup>(4)</sup>	28	919	45.3

Notes

(1) Bimodal product with MWD = 6-7, prepared using single site catalyst.

(2) Monomodal product with MWD = 2.5, prepared using single site catalyst.

(3) Monomodal product with MWD = 3.5, prepared using single site catalyst.

(4) Comparative result for product prepared with Ziegler-Natta catalyst.

- 12 -

Example 5 - Polymer Preparation and Properties

Reactor produced bi-modal LLDPE may be produced as follows:

5

Ethylene, hydrogen and 1-butene comonomer together with the polymerization catalyst  $(nBuCp)_2HfCl_2/MAO$  (supported on silica) are introduced into a loop reactor operated at 80°C and 65 bar. Polymerization parameters are set as follows:  $H_2/C_2$ : 0.4 mol/kmol,  $C_4/C_2$ : 140 mol/kmol. The MFR<sub>2</sub> and density of the product are estimated at 120 g/10min and 937 kg/m<sup>3</sup> respectively.

10

The resulting polymer (still containing the active catalyst) is separated from the reaction medium and transferred to a gas phase reactor where additional hydrogen, ethylene and 1-butene comonomer are added. Polymerization parameters are set as follows:  $H_2/C_2$ : 1-3 mol/kmol,  $C_4/C_2$ : 40-45 mol/kmol. A polyethylene having MFR<sub>2</sub> in the range 30-50 g/10min and density 920-930 kg/m<sup>3</sup> is produced.

15

20

- 13 -

Claims:

1. Use of an LLDPE produced using a single site catalyst in injection moulding of food packaging material.  
5
2. Use as claimed in claim 1 wherein said LLDPE is a metallocene LLDPE (m-LLDPE).
- 10 3. Use as claimed in claim 1 or claim 2 wherein said LLDPE has a MWD in the range of from 2 to 60.
4. Use as claimed in any one of claims 1 to 3 of a said LLDPE for injection moulding of a closure for a food container.  
15
5. Use as claimed in any one of claims 1 to 4 of a said LLDPE having the following characteristics:  
20 MFR<sub>2.16</sub> of from 20 to 100;  
Density of from 910 to 930 kg/m<sup>3</sup>;  
Mw (weight average molecular weight) of from 20 to 100 kD;  
Mn (number average molecular weight) of from 5 to 30 kD;  
25 and  
MWD (i.e. the ratio of the weight average molecular weight to the number average molecular weight): 3 to 10, e.g. 3 to 6.
- 30 6. An injection moulded article formed from an LLDPE produced using a single site catalyst.
7. An article as claimed in claim 6 formed from a metallocene LLDPE.  
35
8. An article as claimed in claim 6 or claim 7 wherein said LLDPE has a MWD in the range of from 2 to 60.

9. An article as claimed in any one of claims 6 to 8 which is an injection moulded closure.

5 10. An article as claimed in claim 9 which is a closure for a food container.

11. An article as claimed in any one of claims 6 to 10 formed from a said LLDPE having the following  
10 characteristics:

MFR<sub>2.16</sub> of from 20 to 100;

Density of from 910 to 930 kg/m<sup>3</sup>;

Mw (weight average molecular weight) of from 20 to 100

15 kD;

Mn (number average molecular weight) of from 5 to 30 kD;  
and

MWD (i.e. the ratio of the weight average molecular weight to the number average molecular weight): 3 to 10,

20 e.g. 3 to 6.

12. An LLDPE suitable for use in injection moulding having a migration level of less than 40mg/dm<sup>2</sup>, preferably less than 10mg/dm<sup>2</sup>, e.g. less than 5mg/dm<sup>2</sup>.

25

13. An LLDPE as claimed in claim 12 being a metallocene LLDPE.

14. An LLDPE as claimed in claim 12 or claim 13 having  
30 the following characteristics:

MFR<sub>2.16</sub> of from 20 to 100;

Density of from 910 to 930 kg/m<sup>3</sup>;

Mw (weight average molecular weight) of from 20 to 100

35 kD;

Mn (number average molecular weight) of from 5 to 30 kD;

and

- 15 -

MWD (i.e. the ratio of the weight average molecular weight to the number average molecular weight): 3 to 10, e.g. 3 to 6.

5 15. Use of an LLDPE in forming an article having a migration level of less than 40mg/dm<sup>2</sup>, preferably less than 10mg/dm<sup>2</sup>, e.g. less than 5mg/dm<sup>2</sup>.

10 16. Use as claimed in claim 15 wherein said LLDPE is a metallocene LLDPE.

17. Use as claimed in claim 15 or claim 16 wherein said article is a closure for a container.

15 18. Use as claimed in any one of claims 15 to 17 wherein said LLDPE has the following characteristics:

MFR<sub>2.16</sub> of from 20 to 100;

Density of from 910 to 930 kg/m<sup>3</sup>;

20 Mw (weight average molecular weight) of from 20 to 100 kD;

Mn (number average molecular weight) of from 5 to 30 kD; and

25 MWD (i.e. the ratio of the weight average molecular weight to the number average molecular weight): 3 to 10, e.g. 3 to 6.

30 19. A closure for a food container, which closure is formed from an LLDPE.

20. A closure as claimed in claim 19 which is formed from a metallocene LLDPE.

35 21. A closure as claimed in claim 19 or claim 20 which is formed from an LLDPE having a migration level of less than 40mg/dm<sup>2</sup>, preferably less than 10mg/dm<sup>2</sup>, e.g. less than 5mg/dm<sup>2</sup>.



- 16 -

22. A closure as claimed in any one of claims 19 to 21 which is associated with a plastic, glass or metal container.

5 23. A closure as claimed in claim 22 which is associated with a polypropylene container.

24. A closure as claimed in any one of claims 19 to 23 wherein said LLDPE has the following characteristics:

10

MFR<sub>2.16</sub> of from 20 to 100;

Density of from 910 to 930 kg/m<sup>3</sup>;

Mw (weight average molecular weight) of from 20 to 100 kD;

15 Mn (number average molecular weight) of from 5 to 30 kD; and

MWD (i.e. the ratio of the weight average molecular weight to the number average molecular weight): 3 to 10, e.g. 3 to 6.

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
20 December 2001 (20.12.2001)

PCT

(10) International Publication Number  
WO 01/96419 A3

- (51) International Patent Classification<sup>7</sup>: C08F 10/02, 210/02, B65D 53/06
- (21) International Application Number: PCT/GB01/02650
- (22) International Filing Date: 14 June 2001 (14.06.2001)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:  
0014547.4 14 June 2000 (14.06.2000) GB
- (71) Applicant (for all designated States except US): BOREALIS TECHNOLOGY OY [FI/FI]; P.O. Box 330, FIN-06101 Porvoo (FI).
- (71) Applicant (for GB only): GOLDING, Louise [GB/GB]; c/o 179 Queen Victoria Street, London EC4V 4EL (GB).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): BAANN, Hege, Vale [NO/NO]; Planetveien 34, N-3942 Skjelsvik (NO). LINDAHL, Ann, Kristin [NO/NO]; Skiensgate 32, N-3912 Porsgrunn (NO).
- (74) Agents: GOLDING, Louise et al.; Frank B. Dehn & Co., 179 Queen Victoria Street, London EC4V 4EL (GB).
- (81) Designated States (national): AE, AG, AL, AM, AT, AT (utility model), AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, CZ (utility model), DE, DE (utility model), DK, DK (utility model), DM, DZ, EC, EE, EE (utility model), ES, FI, FI (utility model), GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SK (utility model), SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.
- (84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).
- Published:
- with international search report
  - before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments
- (88) Date of publication of the international search report: 25 April 2002
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

WO 01/96419 A3

(54) Title: INJECTION MOULDING POLYMER

(57) Abstract: The invention relates to the use of an LLDPE produced using a single site catalyst, e.g. an LLDPE produced using a metallocene (m-LLDPE), in injection moulding of food packaging material, especially closures for food containers. Such materials have been found to exhibit low levels of migration, typically less than 40 mg/dm<sup>2</sup>, e.g. less than 5 mg/dm<sup>2</sup>, and are particularly suitable for use in packaging foods having a high fat content.

# INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 01/02650

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C08F10/02 C08F210/02 B65D53/06

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08F B65D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, PAJ, WPI Data

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 4 424 243 A (NISHIMOTO YOSHIHARU ET AL) 3 January 1984 (1984-01-03) column 2, line 39 -column 2, line 43; examples 1,7	
X	US 5 929 128 A (GREENE EDWARD E ET AL) 27 July 1999 (1999-07-27) the whole document	1-11, 19-24
A	US 5 026 798 A (CANICH JO ANN MARIE) 25 June 1991 (1991-06-25) the whole document	2,7
	-/-	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

\* Special categories of cited documents:

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

- \*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- \*&\* document member of the same patent family

Date of the actual completion of the international search

4 February 2002

Date of mailing of the international search report

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Van Golde, L

# INTERNATIONAL SEARCH REPORT

International Application No  
PCT/GB 01/02650

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	PATENT ABSTRACTS OF JAPAN vol. 1998, no. 11, 30 September 1998 (1998-09-30) & JP 10 147370 A (TOPPAN PRINTING CO LTD), 2 June 1998 (1998-06-02) abstract ---	1
X	WO 98 46409 A (JACOBS IAN ORDE MICHAEL) 22 October 1998 (1998-10-22) page 3, line 4 -page 3, line 17 ---	6-9
X	US 5 925 430 A (MIERZWIAK JAMES G ET AL) 20 July 1999 (1999-07-20) the whole document -----	19-24

# INTERNATIONAL SEARCH REPORT

International application No.  
PCT/GB 01/02650

## Box I Observations where certain claims were found unsearchable (Continuation of item 1 of first sheet)

This International Search Report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:  
because they relate to subject matter not required to be searched by this Authority, namely:
  
2. ☐ Claims Nos.:  
because they relate to parts of the International Application that do not comply with the prescribed requirements to such an extent that no meaningful International Search can be carried out, specifically:
  
3. ☐ Claims Nos.:  
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

## Box II Observations where unity of invention is lacking (Continuation of item 2 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

see additional sheet

1. ☐ As all required additional search fees were timely paid by the applicant, this International Search Report covers all searchable claims.
  
2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
  
3. ☒ As only some of the required additional search fees were timely paid by the applicant, this International Search Report covers only those claims for which fees were paid, specifically claims Nos.:  
1-11, 19-24
  
4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this International Search Report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest.
- ☒ No protest accompanied the payment of additional search fees.

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

This International Searching Authority found multiple (groups of) inventions in this international application, as follows:

1. Claims: 1-11

Use of an LLDPE prepared using a single site catalyst in injection moulding of food packaging material.

2. Claims: 12-18

LLDPE suitable for use in injection moulding having a migration level of 40 mg/square dm.

3. Claims: 19-24

A closure for a food container formed from an LLDPE.

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 01/02650

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4424243 A	03-01-1984	JP 1576889 C	24-08-1990
		JP 57039957 A	05-03-1982
		JP 61000184 B	07-01-1986
		JP 1507652 C	26-07-1989
		JP 56089945 A	21-07-1981
		JP 61001295 B	16-01-1986
		AU 533613 B2	01-12-1983
		AU 6559980 A	16-07-1981
		DE 3064167 D1	18-08-1983
		DK 539480 A ,B,	26-06-1981
		EP 0032027 A2	15-07-1981
US 5929128 A	27-07-1999	US 5849418 A	15-12-1998
		US 5723507 A	03-03-1998
		AU 3970397 A	25-02-1998
		WO 9805731 A1	12-02-1998
		US 6235822 B1	22-05-2001
		AT 204890 T	15-09-2001
		AU 711738 B2	21-10-1999
		AU 1969097 A	01-10-1997
		BR 9708001 A	27-07-1999
		CA 2245735 A1	18-09-1997
		CN 1213390 A ,B	07-04-1999
		DE 69706409 D1	04-10-2001
		EP 0891390 A1	20-01-1999
		ES 2159845 T3	16-10-2001
		JP 2000506820 T	06-06-2000
		NO 984155 A	10-09-1998
		TR 9801808 T2	21-12-1998
		WO 9733935 A1	18-09-1997
		AT 164876 T	15-04-1998
		CA 2169177 A1	23-02-1995
		DE 69409530 D1	14-05-1998
		DE 69409530 T2	06-08-1998
		EP 0714426 A1	05-06-1996
		ES 2114221 T3	16-05-1998
		FI 960719 A	15-04-1996
		JP 9501720 T	18-02-1997
		WO 9505426 A1	23-02-1995
		AT 181351 T	15-07-1999
		CA 2169067 A1	23-02-1995
		DE 69419160 D1	22-07-1999
		DE 69419160 T2	14-10-1999
		DE 714427 T1	28-11-1996
		EP 0714427 A1	05-06-1996
		ES 2089990 T1	16-10-1996
		FI 960720 A	16-02-1996
		GR 96300043 T1	31-08-1996
		GR 3030440 T3	30-09-1999
		JP 9501721 T	18-02-1997
		WO 9505427 A1	23-02-1995
US 5026798 A	25-06-1991	AT 209662 T	15-12-2001
		AU 667292 B2	21-03-1996
		AU 8754291 A	15-04-1992
		BR 9106842 A	20-07-1993
		CA 2090872 A1	14-03-1992
		DE 69132836 D1	10-01-2002

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 01/02650

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5026798	A	EP 0548277 A1	30-06-1993
		JP 6505033 T	09-06-1994
		WO 9205204 A1	02-04-1992
		US 5420217 A	30-05-1995
		US 5504169 A	02-04-1996
		US 5723560 A	03-03-1998
		AT 141275 T	15-08-1996
		AT 151429 T	15-04-1997
		AU 6248390 A	21-03-1991
		AU 643237 B2	11-11-1993
		AU 6443990 A	18-04-1991
		BR 9004537 A	10-09-1991
		BR 9007642 A	21-07-1992
		CA 2024899 A1	14-03-1991
		CA 2065745 A1	14-03-1991
		DD 343767 B1	07-05-1992
		DE 69028057 D1	19-09-1996
		DE 69028057 T3	25-01-2001
		DE 69030442 D1	15-05-1997
		DE 420436 T1	15-02-1996
		DE 662484 T1	27-06-1996
		DK 420436 T3	02-12-1996
		DK 491842 T3	27-10-1997
		EP 0420436 A1	03-04-1991
		EP 0491842 A1	01-07-1992
		EP 0662484 A2	12-07-1995
		EP 0671404 A2	13-09-1995
		EP 0643066 A2	15-03-1995
		ES 2091801 T3	16-11-1996
		ES 2079332 T1	16-01-1996
		GR 3021539 T3	28-02-1997
		GR 3034632 T3	31-01-2001
		HU 55791 A2	28-06-1991
		IL 119415 A	01-06-2000
		JP 3188092 A	16-08-1991
		JP 2994746 B2	27-12-1999
		KR 190735 B1	01-06-1999
		KR 195662 B1	15-06-1999
		NO 178891 B	18-03-1996
JP 10147370	A	02-06-1998	NONE
WO 9846409	A	22-10-1998	AU 6814498 A
			11-11-1998
			WO 9846409 A1
			22-10-1998
			EP 0981431 A1
			01-03-2000
			HU 0102647 A2
			28-12-2001
			TW 397757 B
			11-07-2000
			ZA 9803104 A
			30-10-1998
US 5925430	A	20-07-1999	NONE